Evidence of Performance

Joint sound reduction of filling material

Test Report No. 18-001310-PR01 (PB 01-K05-04-en-01)



Selena Labs Sp.zo.o

ul. Pieszycka 4 58-200 Dzierzoniow Poland

One component PU-Foam Product

Ultra Fast Gun PU Foam Designation

11.1 g/l (width of joint 10 mm)

9.5 g/l (width of joint 20 mm)

Special features

Test 1 (10 mm width of joint) $[R_{s,w}(C; C_{tr}) \ge 63 (-2;-5) dB]$

Test 2 (20 mm width of joint)

 $[R_{\text{sw}}(C; C_{\text{tr}}) \ge 63 \text{ (-2;-5) dB}]$

Weighted sound reduction index of joints R_{s.w} Spectrum adaptation terms C and Ctr

ift Rosenheim 04.06.2018

Bernd Saß, Dipl.-Ing. (FH) Deputy Head of Testing Department **Building Acoustics**

Florian Brechleiter, MSc, Dipl.-Ing. (FH) Operating Testing Officer **Building Acoustics**

Basis

EN ISO 10140-1: 2016 EN ISO 10140-2: 2010 EN ISO 717-1: 2013

Representation



Instructions for use

This procedure is suitable for the comparison of construction products designed for sealing (e.g. gaskets/seals, fillers for joints). The results can be used to evaluate the sound power ratio τ_e according to EN 12354-3 Annex B.

Using the calculated sound reduction of the joint for the calculation of the overall sound reduction is not a substitute for the sound reduction verification of the overall construction.

Validity

The data and results given relate solely to the tested and described specimen.

Testing the sound insulation does not allow any statement to be made on any further characteristics of the construction submitted regarding performance and quality

Notes on publication

The ift Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

The cover sheet can be used as an abstract.

Contents

The test report contains a total of 11 pages:

- Object
- Procedure
- Detailed results
- Instructions for use Data sheet (1 page)



Notified Body 0757 PÜZ-Stelle: BAY 18

